

007-00000000

The polymeric material is hot pressed against the metallic member with
5 sufficient pressure to ensure plastic deformation of the polymeric material. A
fluid tight bond is formed which can withstand pressures of up to 650 psi.